


10.631.161
11.21.2003



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 992 195 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

12.04.2000 Bulletin 2000/15

(51) Int. Cl.⁷: **A23G 1/22**, **A23G 3/02**

(21) Application number: **99202482.8**

(22) Date of filing: **28.07.1999**

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: **23.04.1999 US 298133**

(71) Applicant: **Lekue, S. L.**

08120 La Llagosta (ES)

(72) Inventor:

Llorente Hompanera, José Maria

08120 La Llagosta (ES)

(74) Representative:

Ponti Sales, Adelaida et al

C. Consell de Cent, 322

08007 Barcelona (ES)

Remarks:

A request for correction of the formula on p.6 of the description has been filed pursuant to Rule 88 EPC. A decision on the request will be taken during the proceedings before the Examining Division (Guidelines for Examination in the EPO, A-V, 3.).

(54) **Use of silicone for manufacturing confectionery moulds and baking receptacles in general**

(57) Use of silicone for the manufacturing of confectionery moulds and baking receptacles in general. The silicone may be a heat-curable elastomer of the type intended for applications in contact with foodstuffs, advantageously methyl-vinyl-polysiloxane, and it may be obtained by a process of cross-linking with platinum.

The operation of removal of the baked product from the mould is simplified; further, the moulds can be easily made in any desired shapes and handling of the moulds is improved.

EP 0 992 195 A1

Description

[0001] The present invention relates to the use of silicone for the manufacturing of confectionery moulds and baking receptacles in general.

BACKGROUND OF THE INVENTION

[0002] Silicone is a material of polymeric nature whose chains are made up of alternating oxygen and silicon atoms. Silicones are normally prepared by hydrolysis and subsequent polymerisation of alkylhalogensilanes (both acid- and base-catalysed). The alkylhalogensilanes are in practice made by a direct process, Cu-catalysed, in which the Si reacts with the corresponding alkyl halide. This process provides mixtures of products, whose composition can be modified by a process of redistribution to yield the desired monomer.

[0003] Known in the art are silicone elastomers, which are made up of linear polymers. A cross-linking phase is required in order to provide the elastic properties. The most common elastomers are those deriving from dichloromethylsilane, with molecular weights ranging between 300,000 and 700,000. They are made by a prepolymerisation that provides octamethylcyclotetrasiloxane, purification thereof and subsequent polymerisation in the presence of a small quantity of monofunctional material in order to control the molecular weight, followed by a cross-linking similar to curing, in the presence of peroxides, which lends the material its elastic properties. Other important elastomers are those that contain a small proportion (0.1% molar) of vinyl groups linked to silicon, which undergo much more effective curing, and those that contain between 10 and 15% molar of phenyl groups, and good elastic properties at low temperatures. Elastomers of a much lower molecular weight (10,000 to 100,000) can be obtained by using linear polymer chains ending in silanol groups, which can be cured at room temperature by reaction with an alkoxylane.

[0004] In general, the most important characteristic of the silicone elastomers is the fact that they present a very broad thermal spectrum of use (from -50°C to 200°C) without a significant alteration of their properties. They have good electrical insulation properties, do not self-oxidise or undergo attack by chemical agents in aqueous medium and swell in the presence of non-polar organic solvents, although some special types that contain fluoro- or cyano- groups offer greater resistance to this process.

[0005] Silicone elastomers find their widest industrial application as electrical insulators, fluid-repellents and oxidation protectors, and in the manufacturing of hermetic gaskets. The silicones are highly inert materials, and they repel water. Silicone is inert to chemical agents, with the exception of strong bases and acids, and its toxicity is generally low. The origin of these properties lies essentially in the high stability of the Si-O bond (106 Kcal/mol), and in its strong partial ionic character.

[0006] Other known uses of silicones are in the manufacturing of containers for liquids (such as wineskins) and tubes for transporting substances (such as the tubes used for blood transfusions).

DESCRIPTION OF THE INVENTION

[0007] The present invention is aimed at the use of silicone for the manufacturing of confectionery moulds and the manufacturing of baking receptacles in general.

[0008] The use of silicone for manufacturing confectionery moulds presents many advantages over use of the conventional materials applied in the known confectionery moulds.

[0009] The known moulds are generally manufactured in aluminium, clay or fibreglass. Use of such materials has the disadvantage that, because they are rigid moulds, the mould-removal operation is difficult. Certain types of moulds manufactured in aluminium have had to have their structural complexity increased in order to incorporate a mould-removal system that comprises means of opening of the side wall of the mould in order to take the food out once cooked. Aluminium moulds are thus known whose side wall is articulated so that it can be opened suitably in order to remove the food once cooked. Said moulds have means for locking the side wall in order to keep the side wall closed so that the food retains its shape during cooking.

[0010] The use of silicone to manufacture the confectionery moulds and baking receptacles in general of the invention solves the disadvantages of the confectionery moulds and baking receptacles in the prior art. As will become clear below, the use object of the present invention offers many other advantages which will be set out below.

[0011] The present invention is based on use of a heat-curable elastomer for the manufacturing of confectionery moulds and baking receptacles in general. This heat-curable elastomer is of the type intended for applications involving contact with food.

[0012] The use of silicone has interesting features that afford many advantages, which are set out below.

[0013] Firstly, thanks to the characteristic properties of silicone, the operation of removing a product from the mould is very simple owing to the elasticity that the silicone confers upon the mould or baking receptacle. Users can thus effectively handle said mould or baking receptacle in order to remove the food product from the mould, in the secure knowl-

edge that the mould will recover its initial shape. The characteristics of the silicone provide considerable flexibility of shapes from a constructive viewpoint, so that the moulds and receptacles can be made in any shape and size to suit user requirements.

[0014] Secondly, the heat resistance of the silicone used in the present invention provides highly versatile moulds and baking receptacles, since they can be used in conventional ovens, microwave ovens, and even in freezers. The good physical and chemical stability of the silicone used provides a wide thermal spectrum of use (-40°C to 200°C) and very good resistance to thermal ageing and to oxidating agents (oxygen, ozone, UV).

[0015] Thirdly, the low adherence offered by the silicone surfaces makes moulds and baking receptacles manufactured with the silicone of the invention highly suited to the purposes described.

[0016] Fourthly, the above-mentioned flexibility of the heat-curable elastomer of the type destined for applications in contact with foods of the present invention provides moulds and baking receptacles that can be stored taking up a minimum space. It should be noted that the flexibility of the silicone used is mainly due to the wide angle of the Si-O-Si bond and to the large distance between the Si and O atoms, together with the absence of substituents on the O atom.

[0017] Fifthly, special emphasis should also be placed on the fact that the elastomer in question does not retain much heat. This is important in practice, since it prevents users from burning their hands when handling the mould or receptacle in question.

[0018] In accordance with a first aspect of the invention, the silicone used is of the methyl-vinyl-polysiloxane (VMQ) type.

[0019] The inorganic character of the Si-O-Si chain of the methyl-vinyl-polysiloxane provides an innocuous product and, therefore, one suitable for use with food. It should also be borne in mind that methyl-vinyl-polysiloxane (VMQ) does not alter the taste of foods, while it further has a low concentration of volatile substances, which has a positive influence on the post-curing process of the silicone mould, as will be described below.

[0020] The nature of the polymer provides exceptional mechanical characteristics, as shown in the table below.


<i>Property</i>	<i>Value</i>
Hardness	55 Sh A
Breaking strength	9 Mpa
Elongation	450%
Tear resistance	30 N/mm

[0021] Silicone of the methyl-vinyl-polysiloxane type is fully biocompatible, since it shows no bacterial adhesion due to its capacity for constructing non-polar surfaces which develop minimum interaction with biological systems.

[0022] A mould and/or baking receptacle is thus provided that can be washed easily. In this respect, it should be noted that said mould or receptacle can be washed in a dishwasher.

[0023] All the advantages mentioned above lead to the conclusion that this is a highly advantageous material for use in contact with foodstuffs. For that purpose, and owing to the low concentration of volatile substances, as mentioned above, a short post-curing process is sufficient in order to comply with current legislation on products in contact with foodstuffs.

[0024] In accordance with a second aspect of the present invention, the silicone is obtained by a cross-linking process with platinum, as illustrated below.



[0025] The foregoing formulation illustrates the general schema of a cross-linking reaction by Pt. Thanks to said process the polyaddition reaction takes place much more quickly than reactions initiated by organic peroxides. On the other hand, the use of platinum as a catalyst of the polymerisation process does not generate decomposition by-products. As a consequence, it can be stated that this process does not produce toxic peroxide residues or odours in the cross-linked products. Advantageously, neither are any compounds produced that could alter the taste of foods. For this reason, the type of silicone chosen is totally compatible with the use described in this specification.

[0026] A mould or baking receptacle manufactured in accordance with the present invention is preferably manufactured by moulding the pieces in chromium-plated moulds at a temperature of 190 to 200°C for 3 minutes. Once the piece has been moulded, the post-curing operation is carried out in order to sterilise the piece. Said post-curing operation consists in placing the piece in a hot-air oven or forced-circulation oven at a maximum temperature of about 200°C for 5 hours. Once post-cured, the mould is placed for half an hour in an industrial washer and dryer in order to purify the piece.

[0027] The invention relates to the use of silicone for confectionery moulds and other baking receptacles in general, independently of the shape and dimensions thereof or the accessory details that might arise. It will thus be obvious to an expert in the subject that silicones with organic colorants (suitable for contact with foodstuffs) can be used. As a result, said shapes, dimensions and accessory details may be suitably replaced by others that are technically equivalent, as long as they do not depart from the essential nature of the object of the present invention or from the scope of protection defined by the appended claims.

Claims

1. Use of silicone for the manufacturing of confectionery moulds and baking receptacles in general.
2. Use as claimed in Claim 1, wherein the silicone is a heat-curable elastomer of the type intended for applications in contact with foodstuffs.
3. Use as claimed in Claim 1, wherein said silicone is of the methyl-vinyl-polysiloxane type.
4. Use as claimed in Claim 1, wherein said silicone is obtained by a process of cross-linking with platinum.

European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 20 2482

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 519 372 A (OKAMOTO IND INC) 23 December 1992 (1992-12-23) * page 3, line 33 - line 35; claim 3 *	1,2	A23G1/22 A23G3/02
X	FR 2 747 885 A (MATINOX DECORS) 31 October 1997 (1997-10-31)	1,2	
Y	* page 2, line 20 - line 37 * * page 3, line 32 - line 38 *	3,4	
X	US 4 072 635 A (JERAM EDWARD M) 7 February 1978 (1978-02-07)	1,2	
Y	* the whole document *	3,4	
A	EP 0 637 421 A (FTD FOAM TECH DEV GMBH) 8 February 1995 (1995-02-08) * claim 2; figures *	1	
A	GB 2 254 036 A (BURTON SON & SANDERS LIMITED) 30 September 1992 (1992-09-30)		
A	PATENT ABSTRACTS OF JAPAN vol. 014, no. 134 (C-0701), 14 March 1990 (1990-03-14) & JP 02 009344 A (HANTAA SEIKA KK), 12 January 1990 (1990-01-12)		TECHNICAL FIELDS SEARCHED (Int.Cl.7) A23G
A	US 4 978 696 A (CLARK JOSEPH N ET AL) 18 December 1990 (1990-12-18)		
A	US 4 741 965 A (ZERFASS HANS-RAINER ET AL) 3 May 1988 (1988-05-03)		
A	FR 2 747 886 A (MATINOX DECORS) 31 October 1997 (1997-10-31)		
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 24 November 1999	Examiner Guyon, R
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03 82 (P4/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 20 2482

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

24-11-1999

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0519372	A	23-12-1992	JP 5192636 A	03-08-1993
			JP 4370060 A	22-12-1992
			JP 5057730 A	09-03-1993
			CA 2070729 A	19-12-1992
			GR 93300030 T	24-05-1993
			US 5332190 A	26-07-1994
			AT 152668 T	15-05-1997
			DE 69219516 D	12-06-1997
			DE 69219516 T	21-08-1993
FR 2747885	A	31-10-1997	FR 2747885 A	31-10-1997
US 4072635	A	07-02-1978	DE 2232886 A	18-01-1973
			FR 2144835 A	16-02-1973
			GB 1373055 A	06-11-1974
			JP 55038992 B	07-10-1980
EP 0637421	A	08-02-1995	DE 9310109 U	28-10-1993
GB 2254036	A	30-09-1992	NL 9200584 A	16-10-1992
JP 02009344	A	12-01-1990	NONE	
US 4978696	A	18-12-1990	JP 3121163 A	23-05-1991
US 4741965	A	03-05-1988	DE 3544740 C	04-06-1987
			EP 0226707 A	01-07-1987
			JP 62187781 A	17-08-1987
FR 2747886	A	31-10-1997	FR 2747885 A	31-10-1997

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82